



Competitive Green Technologies

7 Seneca Road, Leamington ON

N8H 5P2, Canada

Phone: + 1 519 329 BLAK (2525)

World-leading biomaterials technology

TECHNICAL DATA SHEET

SEPTEMBER 2019

Product Name: CGTECH – BCR – XX – REV 7.1-6

Product Description:

The properties below are typical of our compostable resins intended for injection molded single serve coffee capsules.

Physical Properties	Typical Values*	Test Method
Melt Flow	8-12 g/min@190°C,2.16Kg	ASTM D1238
Density	1.26 g/cm ³	ISO 1183
Notched Izod Impact @ 20°C	35 J/m	ASTM D256
Tensile Strength @ Yield (50mm/min)	26 MPa	ASTM D638
Tensile Modulus (50mm/min)	2.0 GPa	ASTM D638
Flexural Modulus (14mm/min)	1.20 GPa	ASTM D638
Tensile Elongation at Yield (%) (50mm/min)	12%	ASTM D790
Heat Deflection Temperature (°C)	82	ASTM D648
Moisture Content (%)	≤0.5	ASTM D6980

Note: *Values provided are typical and should not be interpreted as product specification.

The results reported are typical with the caveat that due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability.

This is a patent pending formulation.